

BIZOL Hypoid-Getriebeöl GL5 SAE 85W-140



Martin-Buber-Straße 12, D-14163 Berlin Tel.: +49 30 804 869 - 0 Fax: +49 30 804 869 - 22 sales@bizol.de www.bizol.com

BIZOL Hypoid-Getriebeöl GL5 SAE 85W-140

Classifications and Specifications

Art. 7024

API GL5

ZF TE-ML 05A, 16D, 21A

MIL-L 2105 C

This material and its container must be disposed of in a safe way. Improper disposal of waste oil causes environmental damage. Any addition of foreign substances such as solvents, brake fluid and coolant is prohibited. Safety Data Sheet available for professional users.

200L e



Высококачественное масло трансмиссионное высокого давления из тщательно подобранных базовых масел и многофункциональных присадок высокого давления. Для коробок передач с сервоприводом и главных приводов, особенно подходит для сильно нагруженных гипоидных передач.

Classifications and Specifications

- API GL5
- ZF TE-ML 05A, 16D, 21A
- MIL-L 2105 C

TECHNICAL DATA

Characteristics

ca. Measurement

Температура вспышки	214 °C
Вязкость при 100°C	29,0 мм2/с
Плотность при 15 °C	910 kg/m3
Класс вязкости SAE	85W-140
Номер цвета ASTM	L6
Вязкость при 40°C	415 мм2/с
Зольность сульфатная	0,09 г/100г
Индекс вязкости	98
Температура кипения	-18 °C
Свойства пенообразования	S1B-0/0; S2B-0/0; S3B-0/0
Результат теста с четырьмя шариками	4000/4200 Н
Осевой тест CRC L-37	bestanden
Осевой тест CRC L-42	bestanden
Поташ, оксиды	0,07 г/100г
Вязкость при -12°C	<150.000 мПа с
Показатель нейтрализации, кислоты	1,6 мг KOH/г
Омыление	2,5 мг KOH/г

AVAILABLE PACK SIZE, ARTICLE, LANGUAGES

20 l	7022
60 l	7023
200 l	7024

INSTRUCTIONS

Follow the operation instruction of the vehicle and engine manufacturers.

The statements made in this document are made according to our current knowledge. They do not absolve the user from conducting his or her own examinations. A legally binding assurance of certain properties or suitability for a specific use cannot be derived from our statements. Possibly existing laws and regulations concerning the handling and use of our products have to be observed personally by the user of our products.